

CERTIFICATIONS

- Our procedures work within the very strict standards of AAMA certifications and our innovative pre-treatment process is one of the most environmentally friendly systems available today.

| AAMA Specifications for Paint and Architectural Powder Coat | | | |
|--|------------------------|-------------------------|--------------------------|
| Specification | 2603 | 2604 | 2605 |
| Color retention | 1 year: "slight" fade | 5 yrs fade: Delta E < 5 | 10 yrs fade: Delta E < 5 |
| Chalk resistance | 1 year: "slight" chalk | 5 yrs: Chalk = 8 | 10 yrs: Chalk = 8 |
| Gloss retention | No specification | 5 yrs: 30% retention | 10 yrs: 50% retention |
| Erosion resistance | No specification | 5 yrs: 10% loss | 10 yrs: 10% loss |
| Dry film thickness | 0.8 mils minimum | 1.2 mils minimum | 1.2 mils minimum |
| South Florida Weathering | 1 year | 5 year | 10 year |
| Salt Spray | 1,500 hours | 3,000 hours | 4,000 hours |
| Humidity | 1,500 hours | 3,000 hours | 4,000 hours |